

ADE-TON 2K



BICOMPONENT WATER-BASED PRIMER WITH TONING EFFECT

Water-based bicomponent primer for parquet flooring, applied by roller or brush. To be used as a primer to achieve a toning effect on the treated surface.

TECHNICAL CHARACTERISTICS:

- Bicomponent
- Solvent-free
- Excellent coverage
- Toning effect
- Sandable
- Mixing ratio: 5/1

WHERE IT CAN BE APPLIED:

- Wood flooring
- Wooden surfaces in general (furniture, staircases etc.)

SPECIFIC CHARACTERISTICS (normal conditions):

Appearance:	Opalescent liquid
Viscosity, Ford 4 at 20 °C (seconds): catalysed product	46 - 54
Gloss value at 60 degrees	75 - 85
Mixing ratio:	5: 1
Yield: (g/m ²):	80 - 100 (the yield of the product may vary depending on the porosity or flatness of the surface being treated)
Dry dust free (minutes):	60 - 70
Sanding (hours):	8 - 12
Dry to recoat (hours):	8 - 12
Usage temperature (°C):	+ 15 - +25
Application/Equipment:	Roller, brush
Equipment cleaning:	Water, before the product sets
Product removal:	Water, before the product sets
Storage (months): temperature between +5 °C and +25 °C	12
Disposal information:	Dispose of in compliance with the local and national regulations in force
Packaging:	11 l boxes (2 5-L packs of comp.A + 2 0.5-L packs of comp.B)
Note:	Stir well before use
Usage limitations:	Frost sensitive. Do not apply in damp environments, avoid draughts and bring product up to room temperature before use Always use suitable personal protective equipment Always consult the technical and safety information sheets

SURFACE PREPARATION: The wood floor must be perfectly smooth, filled and sanded, free from loose parts that may interfere with adhesion (e.g. oil, wax, silicone). The surface to be finished must be dry, with 8 to 12% moisture content. Ambient temperature between 15 °C to 25 °C, relative humidity no greater than 75%. After sanding with 150/180 grit, vacuum the whole surface and then clean with an anti-static cloth.

APPLICATION: Leave the product to reach room temperature and stir carefully before use. Slowly add the hardener (component B) to component A, while stirring, and mix carefully. After mixing the two components, wait approximately 10 - 15 minutes before applying. Filter the product before use and apply an even coat using a roller or brush.

Always consult the product data sheet to ensure compatibility of coating systems.

CONTINUE

ADE-TON 2K



MODERATE – HIGH TRAFFIC SYSTEM: 2 COATS OF ADE-TON 2K + 1 COAT OF LIFE VARNISH

APPLICATION: Leave the product to reach room temperature and stir carefully before use. Evenly apply the first coat of the primer using a roller or brush. After approximately 8 - 12 hours in normal conditions, sand using 180 - 220 grit, clean the surface and apply a second coat of the primer. After 8 - 12 hours, sand using 220 grit, clean the surface and, finally, apply a coat of the monocomponent LIFE varnish. Always wear protective gloves. Always consult the technical and safety data sheet for the product.

HIGH TRAFFIC SYSTEM: 2 COATS OF ADE-TON 2K + 1 COAT OF ICE BICOMPONENT VARNISH (matt, semi-matt, semi-gloss and gloss effect)

APPLICATION: Leave the product to reach room temperature and stir carefully before use. Evenly apply the first coat of the primer using a roller or brush. After approximately 8 - 12 hours in normal conditions, sand using 180 - 220 grit, clean the surface and apply a second coat of the primer. After 8 - 12 hours, sand using 220 grit, clean the surface and, finally, apply a coat of the bicomponent ICE varnish. Always wear protective gloves. Always consult the technical and safety data sheet for the product.

HAZARD PICTOGRAMS:

Component A

-- -- --

Component B

