

## EURO GOLD





### LOW-ENVIRONMENTAL-IMPACT BICOMPONENT ADHESIVE FOR WOOD FLOORS

Bicomponent epoxy-polyurethane water-free adhesive, for bonding wood flooring to concrete screeds or on existing non-absorbent floors (marble tiles, terrazzo flooring and wood surfaces).

#### TECHNICAL CHARACTERISTICS:

- Bicomponent
- High performance (adhesion and strength)
- Suitable for all types of wood floors
- Very easy to spread with a trowel
- Highly thixotropic
- Very low VOC emissions
- **High yield**
- Free from water and solvents

#### SPECIAL PROPERTIES:

	Emission class as per French regulations.
	Suitable for underfloor systems

#### WHERE IT CAN BE APPLIED:

- Absorbent and non-absorbent flooring
- Traditional concrete screeds
- Anhydrite screeds (calcium sulphate)
- Absorbent and non-absorbent sub-floors with underfloor heating or cooling systems
- Metallic materials (following an application test)

#### THE FOLLOWING CAN BE BONDED TO THESE SURFACES:

- 10 mm non-interlocking solid wood elements (lamarquet) as per the DIN EN 13227 standard
- Mosaic parquet compliant with standard DIN EN 13488
- (Industrial) solid wood strips compliant with DIN EN 14761 standard
- Interlocking tongue-and-groove solid wood boards with maximum width of 18 cm or 20 cm with oak veneer compliant with standard DIN EN 13226
- Finished multi-layered flooring compliant with standard DIN EN 13489
- Ceramic or stoneware elements

CONTINUE

## EURO GOLD



### SPECIFIC CHARACTERISTICS (normal conditions):

Colour:	Beige to light brown
Mixing ratio A: B::	9: 1
Brookfield viscosity at 20°C (mPa*s):	65,000 - 95,000 Comp. A                      4,000 - 9,000 Comp. B
Brookfield viscosity at 20 °C catalysed product (mPa*s):	50,000 - 75000
Yield: (g/m <sup>2</sup> ):	1000 – 1300 (g/m <sup>2</sup> ) no. 6 notched trowel (product yield may vary depending on the porosity and flatness of the surface being treated)
Usage temperature (°C):	+10 to +30
Open time (minutes):	90 - 120
Ready for walking on (hours):	after 12 - 18 hours, depending on environmental conditions
Final setting (hours):	after 48 - 72 hours (ready-to-walk-on and final setting times vary depending on weather conditions and the thickness of the layer applied)
Tensile shear strength UNI EN 14293 (N/mm <sup>2</sup> ):	4.1 (par. 4.3.4 b)   5.0 (Par. 4.3.4 a)
Wood-Concrete Adhesion (N/mm <sup>2</sup> )	> 3 (Concrete failure)
Shore A hardness:	> 70
Application/Equipment:	notched trowel
Equipment cleaning:	SOLVENTE GR7 solvent, before the product sets
Product removal:	PULITORE LS cleaner, before the product sets
Storage (months): temperature between +5 °C and +25 °C	12
Disposal information:	Dispose of in compliance with the local and national regulations in force Always use suitable personal protective equipment Always consult the technical and safety information sheets
Packaging:	10 kg kits (A + B)
Usage limitations:	Before use, the product should be brought to a temperature of at least 10 °C. Do not apply in damp environments. Do not bond the sides of the panels.
GISCODE:	RE 1 / RU 1

### SURFACE PREPARATION:

The surface to be treated must be compact, dry, clean and free from loose parts such as traces of wall paint, dust, wax and the like, and must be compliant with DIN 18356. Before laying, always use suitable tools to verify the moisture level in the sub-floor and the wood. The moisture level in the sub-floor must be measured in depth (approx. 2-3 cm) using a carbide hygrometer in order to rule out the presence of particularly hygroscopic substances (such as pumice or vermiculite), which could release the moisture contained in them and thus cause the floor surface to swell. The humidity should be <2% for traditional screeds, <0.5% for anhydrite screeds (calcium sulphate) and <0.2% for anhydrite screeds (calcium sulphate) with radiant heating. The moisture content of the wood must be between 7 and 11%. Do not apply on screeds that are not protected from possible rising damp (always ensure there is an appropriate vapour barrier between the screed and flooring). On low-porosity or calcium sulphate screeds, mechanical sanding of the surface is recommended, and any residual dirt, dust or loose parts must be vacuumed off the surface. Dusty concrete sub-floors or sub-floors with moisture must be consolidated with primers (e.g. our PRIMER HE, PRIMER WB PU or PRIMER PA 400 products), to optimise adhesion of the glue (see technical data sheet).

### APPLICATION:

Apply at an ambient temperature of between 10 °C and 30 °C, otherwise viscosity and drying times may vary significantly, with less-than-optimal results. Allow the product to reach room temperature before use. Pour component B into the container of component A, and mix thoroughly with a low-speed stirrer to obtain an even paste uniform in colour. Spread the mix using a notched trowel, incorporating any powder on the sub-floor. Lay the parquet, pressing the flooring down firmly to ensure that the adhesive sticks to the whole surface. It is recommended that wood flooring is kept at a distance of at least 8-10 mm from the walls.

Before the product sets, remove any residual adhesive by using a cloth soaked in our PULITORE LS cleaner. You should always check that the cleaning agent is compatible with the surface being treated. Always consult the product's technical and safety information sheets before use.

### HAZARD PICTOGRAMS:

#### Component A



#### Component B

