



FACILE PRO

MONOCOMPONENT VARNISH

Water-based monocomponent satin-finish varnish for wooden floors. Easy to apply and excellent final result.

TECHNICAL CHARACTERISTICS:

- Monocomponent
- Solvent-free
- Water-based
- Satin-finish
- High-resistance

WHERE IT CAN BE APPLIED:

- Wood flooring
- Wooden surfaces in general (furniture, staircases etc.)

SPECIFIC CHARACTERISTICS (normal conditions):

Appearance:	Milky liquid
Viscosity, Ford 4 at 20°C (seconds):	40 - 60
Gloss value at 60°:	Satin finish: 30-40 gloss
Yield: (g/m ²):	80 - 100 (The product yield may vary depending on the porosity or flatness of the surface to be treated)
Dry dust free (minutes):	60 - 70
Sanding (hours):	8 - 12
Final setting (days):	5 - 7
Ready for walking on (days)	2 - 3
Usage temperature (°C):	+ 15 - +25
Application/Equipment:	Roller, brush
Equipment cleaning:	Water, before the product sets
Product removal:	Water, before the product sets
Storage (months): temperature between +5°C and +25°C	12
Disposal information:	Dispose of in compliance with the local and national regulations in force
Packaging:	10 L kits (containers of 5 litres each)
Note:	Stir well before use
Usage limitations:	Frost sensitive. Do not apply in damp environments, avoid draughts and bring product up to room temperature before use Always use suitable personal protective equipment Always consult the technical and safety information sheets

SURFACE PREPARATION: The wood floor must be perfectly smooth, filled and sanded, free from loose parts that may interfere with adhesion (e.g. oil, wax, silicone). The surface to be finished must be dry, with 8 to 12% moisture content. Ambient temperature between 15 °C to 25 °C, relative humidity no greater than 75%. After sanding with 120/150 grit, vacuum the whole surface and then clean with an anti-static cloth.

APPLICATION: Leave the product to reach room temperature and stir carefully before use. Filter and apply an even coat using a roller or brush.

Always consult the product data sheet to ensure compatibility of coating systems.

Always wear protective gloves. Always consult the technical and safety data sheet for the product.

CONTINUE



FACILE PRO

MODERATE TRAFFIC SYSTEM: PU-1 BASIC + FACILE PRO

APPLICATION: Leave the product to reach room temperature and stir carefully before use. Apply the first coat of PU-1 BASIC evenly using a roller or brush. After 6-8 hours (without sanding), apply a second coat of PU-1 BASIC. After approximately 12 hours, sand using 180-220 grit, clean the surface and apply a coat of FACILE PRO varnish.

MODERATE TRAFFIC SYSTEM (just varnish): FACILE PRO

APPLICATION: Leave the product to reach room temperature and stir carefully before use. Evenly apply the first coat of FACILE PRO with a roller or brush. After approximately 8-12 hours, sand using 180-220 grit, clean the surface and apply a second coat of FACILE PRO. Then, if necessary and always after sanding, apply a third and final coat of FACILE PRO.

HAZARD PICTOGRAMS:

-- -- --