



NO-TANNINO

ANTI-TANNIN BASE

Water-based, anti-tannin, non-yellowing monocomponent base for treating wooden surfaces.

TECHNICAL CHARACTERISTICS:

- Monocomponent, ready for use
- Anti-tannin and non-yellowing
- High-penetration
- **Also available in white**

WHERE IT CAN BE APPLIED:

- Wood flooring
- Wooden surfaces in general (furniture, staircases etc.)

SPECIFIC CHARACTERISTICS (normal conditions):

Appearance:	Milky liquid
Viscosity, Ford 4 at 20°C (seconds):	23 - 27
Colour:	Transparent or white
Yield: (g/m ²):	90 - 100 (The product yield may vary depending on the porosity or flatness of the surface to be treated)
Dry dust free (minutes):	90 - 120
Dry to recoat (hours):	8 - 12
Total drying time (hours):	18 - 24
Usage temperature (°C):	+ 15 - +25
Application/Equipment:	Roller, brush
Equipment cleaning:	Water, before the product sets
Product removal:	Water, before the product sets
Storage (months): temperature between +5°C and +25°C	12
Disposal information:	Dispose of in compliance with the local and national regulations in force
Packaging:	10 L boxes (2x 5 L containers)
Note:	Stir well before use
Usage limitations:	Frost sensitive. Do not apply in damp environments, avoid draughts and bring product up to room temperature before use Always use suitable personal protective equipment Always consult the technical and safety information sheets

SURFACE PREPARATION: The wood floor must be perfectly smooth, filled and sanded, free from loose parts that may interfere with adhesion (e.g. oil, wax, silicone). The surface to be finished must be dry, with 8 to 12% moisture content. Ambient temperature between 15 °C to 25 °C, relative humidity no greater than 75%. After sanding with 120/150 grit, vacuum the whole surface and then clean with an anti-static cloth.

APPLICATION: Leave the product to reach room temperature and stir carefully before use. Evenly apply a first coat of NO TANNINO primer with a roller or brush. After approximately 6-8 hours in normal conditions, sand lightly using 180-220 grit, clean the surface and then apply a second coat of the NO TANNINO primer. After 24 hours, always after sanding, apply a third and final coat of one of our water-based monocomponent or bicomponent varnishes (see the technical data sheets). Always wear protective gloves. Always consult the technical and safety data sheet for the product.

HAZARD PICTOGRAMS:

-- -- --

CONTINUE