



## PAVI-CRYL

### HIGH-PENETRATION DUST-REPELLENT PRIMER

Dust-repellent primer in water dispersion specifically formulated for friable or dusty screeds, smoothing concrete or anhydrite screeds. **Product suitable for use with reactive glues, both monocomponent silane adhesives and bicomponent epoxy-polyurethane or polyurethane adhesives.**

#### TECHNICAL CHARACTERISTICS:

- Water-based monocomponent
- Ready for use
- Dust-repellent for concrete screeds
- For indoor use

#### WHERE IT CAN BE APPLIED:

- Traditional concrete screeds
- Anhydrite screeds (plaster)
- Sub-floors with heating or cooling system

#### DO NOT USE:

- On non-absorbent bases (glass, marble, tiles, etc.)
- On surfaces subject to continual rising damp that are not protected by a vapour seal barrier

#### SPECIFIC CHARACTERISTICS (normal conditions):

Appearance:	Milky liquid
Viscosity, Ford 4 at 20 °C (seconds):	10 - 12
Dry (%):	13.5 - 15.5
Yield: (g/m <sup>2</sup> ):	100 - 150
Working life (minutes):	5 - 20
Usage temperature (°C):	+15 - +25
Time before use (days):	1 - 3
Film setting (hours):	3 - 5
Application/Equipment:	Roller, brush
Equipment cleaning:	Water, before the product sets
Storage (months): maximum temperature +5 °C	12
Disposal information:	Dispose of in compliance with the local and national regulations in force
Packaging:	10 Kg
Recommendations for use:	Do not apply in damp environments Frost sensitive Always use suitable personal protective equipment Always consult the technical and safety information sheets Allow the product to reach 20 °C before applying

#### SURFACE PREPARATION:

Always use suitable tools to check the moisture content in the sub-floor. The sub-floor must be compact, free from moisture and with loose parts, such as chalk, dust, oil or wax residue cleaned off.

#### APPLICATION:

Allow the product to reach 20 °C before use. The product is ready for use. Apply evenly across the sub-floor with a roller or brush without piling up too much product in one place. Always check the moisture content of the screed before bonding (<2% (<0.5% anhydrite). Ambient temperature between 15 °C to 25 °C, relative humidity no greater than 75%. Always use suitable personal protective equipment. Always consult the technical and safety data sheet for the product.

#### NOTES:

Avoid piling up too much product in one place as this may affect the adhesion of adhesives applied on top.

#### HAZARD PICTOGRAMS:

-- -- --